

Technical Data Sheet



Date 17/01/12

Grade: A500G HiPerm® Plus

Filter Media Description Low resistance HEPA filter medium composed of borosilicate microfibers with an acrylic resin binder. Designed to be processed in minipleat applications.

CLASSIFICATION(S): EN1822 H13 @ 2.5 cm/s

Test Description	Units	Target	Specification	Test condition
BASIS WEIGHT:	g/m ²	78	73 - 83	
THICKNESS	mm	0.52		2 kPa pressure
AIRFLOW RESISTANCE	Pa	330	300 - 363	5.33 cm/sec
PENETRATION	%	0.008	.017 max	2.5 cm/sec .16um
TENSILE STRENGTH MD:	kN/m	1.2	0.9 min	
TENSILE STRENGTH CD:	kN/m	0.75	0.45 min	
GURLEY STIFFNESS MD:	gu	1000	750 - 1250	
IGNITION LOSS:	%	5.6	4.0 - 7.2	
WATER REPELLENCY:	kPa	8.5	5.0 - 12.0	1 kPa / min
FLAMMABILITY DATA:			M1	NF P 92-503 (1995)

Actual filtration performance, i.e. efficiency and dust holding capacity, will vary depending upon filter design parameters and the normal variation of the media properties consistent with the specification range. We continuously strive to define our products and hence the specifications are subject to change.



Hollingsworth & Vose Company

Engineered Papers & Nonwovens - Established 1643

www.hollingsworth-vose.com

P.O. Box 168, 219 Townsend Road, West Groton, MA 01472 USA

tel 1-978-448-3311

fax 1-978-448-3090